



## PVDF Powder 201

### Technical Index

Item	Unit	201
Appearance	/	White powder
Odor	/	Without
Purity, ≥	%	99.5
Scattered fineness, ≤	μm	25
Melting Index	g/10min	0.5-2.0
Standard relative density	g/cm <sup>3</sup>	1.75-1.77
Melting point	°C	156~165
Thermal decomposition, ≥	°C	410
moisture, ≤	%	0.10

### Main Application

The resin is used to produce Fluorocarbon coating as fluorocarbon resin.

### Attention

Keep this product from high temperature to prevent toxic gas releasing at the temperature above 350°C

### Package, transportation and storage

- 1). Packed in plastic drums, and circular barrels outside, 20kg/drum.
- 2). Stored in clear and dry places, and temperature range is 5-30°C.
- 3). The product should be transported as non-dangerous product, avoiding heat, moisture and strong shock.